Western Hemlock

FACTSHEET

{Tsuga heterophylla}

Western Hemlock is the single most plentiful tree species on the coast of British Columbia (B.C.). It grows along both the east and west sides of the coastal mountain ranges, from sea level to mid elevations, as well as in the interior of the province.

On average it typically grows 30 to 50 metres tall and 1 to 1.5 metres in diameter. It seldom grows in pure stands, usually mixed with Douglas Fir, Amabilis Fir, Sitka Spruce, and Western Red Cedar. Of B.C.'s total growing stock, Hemlock makes up 17.7% of the volume and close to 60% of the coastal volume.

COMMON USES

The wood of Hemlock is firmly established as an outstanding wood for moldings and interior woodworking. Other uses include doors, windows, floors, suspended ceilings, ladders, and other purposes where a high grade is needed.

Hemlock is also used for general construction, roof decking and plywood. It is used for laminating stock and the production of glue-laminated beams.

OF INTEREST

- Western Hemlock is known for its even density which provides for excellent machining properties.
- Hemlock lumber is seasoned uniformly in dry kilns to a moisture content of 19% or 10-12% depending on the end use. Kiln drying inhibits natural staining of the wood, improves its strength and stiffness, enhances its appearance, and increases its resistance to decay and attack by insects.

PHYSICAL PROPERTIES		
STIFFNESS/ MOE (MPa)	Air Dry	12300
STRENGTH/MOR (MPa)	Air Dry	81
DENSITY (kg/m ³)	Air Dry	429
COMPRESSION PARALLEL (MPa)	Air Dry	46.7
SHEAR (MPa)	Air Dry	6.48
SHRINKAGE (air dried - 12%)	Tangential / Radial ratio	1.6



WORKING PROPERTIES

Hemlock has a relatively good strengthto-weight ratio and is known for its excellent working properties. The wood requires special care when drying but yields quality product. It is relatively easy to work, with good machining qualities. It turns, planes and shapes well and can be sanded to a smooth finish. The wood glues satisfactorily, has moderate nail and screw holding ability and polishes beautifully.

WORKING PROPERTIES			
	PROCESS	PERFORMANCE	COMMENTS
MACHINING	Planing	Good to average	Silky smooth finish easy to achieve.
	Shaping	Average	Easy, with good surface quality.
	Sanding	Good	Good sanding finish.
FASTENING	Screwing	Good	
	Nail Retention	Good	
	Gluing	Average	
FINISHING	Staining	Good	Best finish is with light stain or clear finish followed by nitrocellulose alkyd clear sealer and finish.
	Painting	Good	
DRYING	Ease of Drying	Fair	Due to the high moisture content of this wood, longer kiln drying times are required. When dried at hightemperatures the exterior 2-3mm can turn a brownish colour.
DURABILITY	Natural Decay Resistance	Poor	Not appropriate for prolonged outdoor exposure.
	Treatability	Good	Can be improved by incising.



FOR MORE INFORMATION ON THE AVAILABILITY OF WESTERN HEMLOCK, PLEASE CONTACT INFO@CANADIANWOOD.COM.VN

TRY CANADIAN WOOD HÃY DÙNG THỬ GÕ CANADA canadianwood.com.vn +84 (0)274 380 3609



Data for this factsheet has been compiled by FPInnovations from internal and external scientific sources. FPInnovations is a not-for-profit technical research institute serving the Canadian forest sector.